

# **INSTRUCTION OF USE: Sinomer Kalt N**

### Material information and manufacturer data

Name, trade name	Sinomer Kalt N			MD				
Classification	Classification:	lla	Labelling:	C€	0483	MD	☐ Technical Device	
Data	Article No.:	A04<>			Basis UDI:		763029670101P	
	Powder			Liquid			Colours	
Variants	500g, 1.000g, 5.0	000g	250ml, 500	250ml, 500ml, 1.000ml, 2.500ml			Rosa, Clear, Rosa V	
Allowed equipment	Can be applied to metal alloys or metal frameworks and underlaid with adhesive bond and opaquer. (Duropont Silan, Duropont Opaker), as well as combinable with metal clasps and artificial teeth.							
	SRN:		LI-MF-00000633					
Manufacturer data	Anschrift:	^	NOVODENT Ets., Industriestrasse 32, 9487 Bendern, Liechtenstein					
General information	The product may only be used by qualified personnel such as dental technicians and dentists. Immediately upon receipt of the product, please file the product name and Lot No. in your administration. For each work produced, make a note of all products used with all Lot Nos. For the protection of you, your patients and the environment, please follow the instructions on the Instructions for Use.							
Intended purpose	For the fabrication of prosthetic restorations in full and partial dentures							
Indication	For plugging and pressing technique as well as injection technique: Partial removable dentures and total dentures							
Contraindication	Avoid direct contact of non-polymerised material in the intraoral area. In case of hypersensitivity of the patient to any of the ingredients, refrain from use.							

### Use of the product

### **Properties**

Two-component denture material powder + liquid, recipe free of methyl methacrylate monomer and free benzoyl peroxide. According to current knowledge, this base material is toxicologically harmless and can be described as low allergy. For sensitised persons, the suitability of Sinomer cold N should be tested with a platelet in the mouth for approx. 72 hours.

After completion, the denture can be stored in warm water or olive oil (approx. 30°C) for another 24-48 hours to remove traces of monomer from the processing.

Environmer	nt of use		Shelf life and storage instructions				
Bei Raumtemperatur Anwendbar. Von Zündquellen fernhalten.			Avoid direct sunlight. Always keep containers closed. The shelf life is 3 Years. Do not use the				
Material composition			product after the expiry date. Keep out of reach of children. Store at room temperature min. + 2°C,				
Powder Liquid:		yl methacrylate , polyurethane dimethacrylate	max. 25°C.				
Skin protec	tion	Disposable gloves nitrile rubber, layer the	thickness 0.7mm, penetration time (min) >480 thickness 0.4mm, penetration time (min) >120 obtained from the manufacturer of the protective gloves				
Transport For regulations on the transport of the data sheets.			raw material, please refer to the Sinomer Kalt N safety				
Specification	ns	For specific product specifications, plea	ase refer to the Sinomer Kalt N technical data sheet.				

### Regulatory information SN EN ISO 20795-1

During polishing, small amounts of monomer may be released on the surface, which may cause skin sensitisation in sensitised (sensitive) patients. In case of irritation or known allergy to any of the ingredients, the product should not be used.



# Instructions for use

Mixing ratio	1.1 - 1.3 parts by weight powder to 1 part by weight liquid. (e.g. 1.1g - 1.3g powder to 1g liquid)								
Polymerisation	Device	Pressure pot	Pressure	4 – 6 bar	Duration	15 – 20 Minuten	Temperature	40 – 45°C	
Processing	The plas Universal Artificial 1 retentions aesthetic The produsing a some Then polymeris according Note on Pre-polish hair brush Caution:	teeth should be so should be coareffects.  uct (raw material cale and mix we can the compoundation, the workput to the state of the polishing of the and a small potential teeth can the can and a small potential teeth can the can t	roughened lated with a pull), should be lell for 30 second into the police is removed art.  I mandrel or lishing fork.  In quickly los	e used at roonds. Allootting and oved from	e, undercut an as Duropor  coom temper  w to bubble I place it im the pressure  cachment. The	oided.  and wetted vertical to accept the second se	vith acetone. Me chieve an optimal the powder with 30 seconds) and not the pressure bund, finished an with a pumice sto vily polished.	atal clasps, al hold and in the liquid mix again. pot. After d polished ne, a goat	

# Liability notice

The information is based on the current state of our knowledge, but does not constitute a guarantee of product properties and does not establish a contractual legal relationship. The product is normally delivered stabilised. However, it may polymerise under heat development if the storage time and/or storage temperature are significantly exceeded. No liability is accepted for damage resulting from failure to observe the instructions for use and the area of application. This also applies if the product is mixed or processed together with products from competitors.

Contact details of the manufacturer								
Address:	PSS: NOVODENT Ets., Industriestrasse 32, 9487 Bendern, Liechtenstein							
Contact:	Phonel.: +423	3 377 1500	Fax:	+423 377	1509	E-Mail:	frontoffice@novodent.com	
Websites::	Webshop: www.novodent.c		nt.dental	Main page:			www.novodent.com	

Note about the symbols ①								
LOT	☑ Lot/Batch No.	•••		UDI	☐ Unique Device Identification			
		Ĵ.		[]i	☐ Observe operating instructions			
REF		类	☐ Protection from sunlight	MD	☑ Medical Device *			
<b>(!)</b>			☐ Danger Flammable (GHS)	MAC	☐ No Medical Device			
SRN	Single Registration N     Single Re	lumber (EU	DAMED)	CE	☑ MP- European conformity *			

Symbols used on the labelling of this product are marked with 

 ∴ \*Not applicable for non-medical products