





INSTRUCTION OF USE: Sinomer HC Paste

Material information and manufacturer data

Name, trade name	Sinomer HC Paste						<input checked="" type="checkbox"/> Medical Device
Classification	Classification:	Ila	Labelling:	CE	0483		<input type="checkbox"/> Technical Device
Data	Article No.:	A71<>		Basis UDI:		763029670102P	
Variants	Powder		Paste			Colours	
	-		500g, 1.000g (2x500g)			Rosa, Clear, Rosa V	
Allowed equipment	Can be applied to metal alloys or metal frameworks and underlaid with adhesive bond and opaquer. (Duropont Silan, Duropont Opaker), as well as combinable with metal clasps and artificial teeth.						
Manufacturer data	SRN:		LI-MF-000000633				
	Anschrift:		NOVODENT Ets., Industriestrasse 32, 9487 Bendorf, Liechtenstein				
General information	The product may only be used by qualified personnel such as dental technicians and dentists. Immediately upon receipt of the product, please file the product name and Lot No. in your administration. For each work produced, make a note of all products used with all Lot Nos. For the protection of you, your patients and the environment, please follow the instructions on the Instructions for Use.						
Intended purpose	For the fabrication of prosthetic restorations in full and partial dentures						
Indication	For plugging and pressing technique as well as injection technique: Partial removable dentures and total dentures						
Contraindication	Avoid direct contact of non-polymerised material in the intraoral area. In case of hypersensitivity of the patient to any of the ingredients, refrain from use.						

Use of the product

Properties	
A one-component prosthetic material (paste), prescription-free, without methyl methacrylate monomer and free benzoyl peroxide. Based on current knowledge, this base material is considered toxicologically harmless and low-allergenic. For sensitized individuals, the suitability of Sinomer Cold N should be tested by placing a small plate in the mouth for about 72 hours. After completion, the prosthesis can be stored for another 24-48 hours in warm water or olive oil (around 30°C) to remove any monomer traces from processing.	
Environment of use	
Bei Raumtemperatur Anwendbar. Von Zündquellen fernhalten.	
Material composition	
Powder	Polymethyl methacrylate
Liquid:	Oligomer, polyurethane dimethacrylate
Skin protection	Disposable gloves butyl rubber, layer thickness 0.7mm, penetration time (min) >480
	Disposable gloves nitrile rubber, layer thickness 0.4mm, penetration time (min) >120 The exact penetration time must be obtained from the manufacturer of the protective gloves and must be observed.
Transport	For regulations on the transport of the raw material, please refer to the Sinomer HC Paste safety data sheets.
Specifications	For specific product specifications, please refer to the Sinomer HC Paste technical data sheet.

Regulatory information	SN EN ISO 20795-1
During polishing, small amounts of monomer may be released on the surface, which may cause skin sensitisation in sensitised (sensitive) patients. In case of irritation or known allergy to any of the ingredients, the product should not be used.	



Instructions for use

Mixing ratio	not applicable							
Polymerisation	Device	Press, cooking pot	Pressure	300kg/cm ³	Duration	30 Minutes	Temperature	100°C
Processing	<u>Preparation and use</u> The plaster model is to be insulated with a suitable insulation such as Seperator CC or HC Universal. Insulations containing formaldehyde should be avoided.							
	Artificial teeth should be roughened before use, undercut and wetted with acetone. Metal clasps, retentions, should be coated with a primer such as Duropont Silan to achieve an optimal hold and aesthetic effects.							
	Place the material in the cuvette and press to a maximum of 300 kg/cm ³ and fix it with a clamp. Place the flask with the clamp in 100 °C water. As soon as the water boils again (100 °C) leave it in the water for 30 minutes. Then allow to cool in the air for at least 30 minutes (warm to the touch) and then carefully devest. Finish and grind the denture according to the general state of the art. Repairs and relinings can be carried out with the cold polymer Sinomer cold N or rebased with the hot polymer.							
	<u>Note on polishing</u> Pre-polish with an emery mandrel or rubber attachment. Then polish with a pumice stone, a goat hair brush and a small polishing fork.							
	Caution: Artificial teeth can quickly lose their aesthetic appearance if heavily polished.							
Polish carefully with a polishing fork. Auxiliaries such as approved polishing agents for dental acrylics can be used.								

Liability notice

The information is based on the current state of our knowledge, but does not constitute a guarantee of product properties and does not establish a contractual legal relationship. The product is normally delivered stabilised. However, it may polymerise under heat development if the storage time and/or storage temperature are significantly exceeded. No liability is accepted for damage resulting from failure to observe the instructions for use and the area of application. This also applies if the product is mixed or processed together with products from competitors.

Contact details of the manufacturer

Address:	NOVODENT Ets., Industriestrasse 32, 9487 Bendern, Liechtenstein					
Contact:	Phonel.:	+423 377 1500	Fax:	+423 377 1509	E-Mail:	frontoffice@novodent.com
Websites::	Webshop:	www.novodent.dental			Main page:	www.novodent.com
SSCP Rapport	https://sscp.novodent.com/prothesenkunststoffe.pdf					

Note about the symbols ⓘ

	<input checked="" type="checkbox"/> Lot/Batch No.		<input checked="" type="checkbox"/> Manufacturer		<input checked="" type="checkbox"/> Unique Device Identification
	<input checked="" type="checkbox"/> Expiry date		<input checked="" type="checkbox"/> Storage temperatures		<input checked="" type="checkbox"/> Observe operating instructions
	<input checked="" type="checkbox"/> Articulenumber		<input type="checkbox"/> Protection from sunlight		<input checked="" type="checkbox"/> Medical Device *
	<input checked="" type="checkbox"/> Attention (GHS)		<input type="checkbox"/> Danger Flammable (GHS)		<input type="checkbox"/> No Medical Device
SRN	<input checked="" type="checkbox"/> Single Registration Number (EUDAMED)				<input checked="" type="checkbox"/> MP- European conformity *

ⓘ Symbols used on the labelling of this product are marked with ☒. *Not applicable for non-medical products